

16. (Amended) A base body for a photosensitive drum according to claim 49, wherein said flake inorganic material is in the form of flakes each having an aspect ratio (length/thickness) in a range of 10 to 70.

B2 17. (Amended) A base body for a photosensitive drum according to claim 49, wherein said flake inorganic material is one kind or two or more kinds selected from aluminum flakes, Ni-coated mica, muscovite, and phlogopite.

18. (Amended) A base body for a photosensitive drum according to claim 49, wherein a content of said flake inorganic material is in a range of 10 to 25 wt%.

B3 23 (Twice Amended) A base body for a photosensitive drum, which is obtained by molding a conductive resin composition into a cylindrical shape, wherein said resin composition consists essentially of polyamide resin and has a factor $\tan\delta$ in a range of 0.05 or more.

B4 36. (Amended) A photosensitive drum comprising:
a cylindrical base body, which is obtained by molding a conductive resin composition into a cylindrical shape; and
a photosensitive layer formed on an outer peripheral surface of said cylindrical base body;
wherein said resin composition comprises an inorganic filler for reinforcement, and said inorganic filler for reinforcement is a micro-spherical inorganic material in the form of spherical particles having an average particle size in a range of 50 μm or less.

40. (Amended) A photosensitive drum according to claim 50, wherein said flake inorganic material is in the form of flakes each having an aspect ratio (length/thickness) in a range of 10 to 70.

B5 41. (Amended) A photosensitive drum according to claim 50, wherein said flake inorganic material is one kind or two or more kinds selected from aluminum flakes, Ni-coated mica, muscovite, and phlogopite.

42. (Amended) A photosensitive drum according to claim 50, wherein a content of said flake inorganic material is in a range of 10 to 25 wt%.

B6 47. (Twice amended) A photosensitive drum comprising:
a cylindrical base body, which is obtained by molding a conductive resin composition into a cylindrical shape; and
a photosensitive layer formed on said cylindrical base body;
wherein said resin composition consists essentially of polyamide resin and has a factor $\tan\delta$ in a range of 0.05 or more.

Please add the following new claims:

B7 --49. (New) A base body for a photosensitive drum, which is obtained by molding a conductive resin composition into a cylindrical shape,
said resin composition comprising an inorganic filler for reinforcement,
wherein said inorganic filler for reinforcement is a flake inorganic material.

--50. (New) A photosensitive drum comprising:

SUPPLEMENTAL AMENDMENT UNDER 37 C.F.R. § 1.111
USSN 09/988,283

a cylindrical base body, which is obtained by molding a conductive resin composition into a cylindrical shape; and

B7
Control
a photosensitive layer formed on an outer peripheral surface of said cylindrical base body;

wherein said resin composition comprises an inorganic filler for reinforcement, and said inorganic filler for reinforcement is a flake inorganic material.